



# TEST REPORT

Test Report # 18H-001496 Date of Report Issue: March 9, 2018  
 Date of Sample Received: March 5, 2018 Pages: Page 1 of 12

## CLIENT INFORMATION:

Company: Numo Manufacturing  
 Recipient: Rebecca Williams  
 Recipient Email: rwilliams@numomfg.com



## SAMPLE INFORMATION:

Description: Nylon Cloth - Navy, White, Purple, Royal, Green, Pink, Turquoise, Tan, Burgundy, Silver, Orange  
 Assortment: - Purchase Order Number: -  
 SKU/style No.: - Toy Co./Agency: -  
 Factory/Supplier/Vendor: Numo Manufacturing Country of Origin: China  
 Country of Distribution: - Labeled Age Grade: -  
 Quantity Submitted: 1 lot Recommended Age Grade: -  
 Testing Period: 03/06/2018 – 03/09/2018 Tested Age Grade: -

## OVERALL RESULT:

**PASS**

Refer to page 2 for test result summary and appropriate notes.

ANSECO GROUP (HK) LIMITED

Loska Yeung Lok Ka  
 Assistant Manager, Chemical Laboratory

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



---

**TEST RESULTS SUMMARY:**

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	CPSIA Section 101, Total Lead in Substrate Materials
PASS	Client's Requirement, Total Cadmium in Substrate Materials
PASS	CPSIA Section 108, Phthalates – Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP)
PASS	California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

**DETAILED RESULTS:****CPSIA Section 101, Total Lead in Substrate Materials**

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	2	3	4	5	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

Specimen No.	6	7	8	9	10	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

Specimen No.	11	---	---	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	---	---	---	---	100
<b>Conclusion</b>	PASS	---	---	---	---	

**Note:**

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****Client's Requirement, Total Cadmium in Substrate Materials**

Test Method: ASTM F963-16 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	2	3	4	5	Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Cadmium (Cd)	ND	ND	ND	ND	ND	<b>40</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

Specimen No.	6	7	8	9	10	Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Cadmium (Cd)	ND	ND	ND	ND	ND	<b>40</b>
<b>Conclusion</b>	PASS	PASS	PASS	PASS	PASS	

Specimen No.	11	---	---	---	---	Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Cadmium (Cd)	ND	---	---	---	---	<b>40</b>
<b>Conclusion</b>	PASS	---	---	---	---	

**Note:**

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****CPSIA Section 108, Phthalates – Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		1	2	3	4	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
<b>Conclusion</b>		PASS	PASS	PASS	PASS	

**Note:**

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****CPSIA Section 108, Phthalates – Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		5	6	7	8	
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
<b>Conclusion</b>		PASS	PASS	PASS	PASS	

**Note:**

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****CPSIA Section 108, Phthalates – Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		9	10	11	---	
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	---	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	---	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	---	1000
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	ND	---	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	---	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	---	1000
<b>Conclusion</b>		PASS	PASS	PASS	---	

**Note:**

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		1	2	3	4	Limit (ppm)
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	1000
<b>Conclusion</b>		PASS	PASS	PASS	PASS	

**Note:**

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**Remark:**

The specification is quoted from client's requirement.



**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		5	6	7	8	
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	ND	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	ND	1000
<b>Conclusion</b>		PASS	PASS	PASS	PASS	

**Note:**

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**Remark:**

The specification is quoted from client's requirement.

**DETAILED RESULTS:****California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)**

Test Method: CPSC-CH-C1001-09.3

Analytical Method: Gas Chromatography with Mass Spectrometry

Specimen No.		9	10	11	---	
Test Item	CAS No.	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	ND	---	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	ND	---	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	ND	---	1000
Diisononyl phthalate (DINP)	28553-12-0 68515-48-0	ND	ND	ND	---	1000
Diisodecyl phthalate (DIDP)	26761-40-0 68515-49-1	ND	ND	ND	---	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	ND	---	1000
<b>Conclusion</b>		PASS	PASS	PASS	---	

**Note:**

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 120 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**Remark:**

The specification is quoted from client's requirement.

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
1	Blue textile	Cloth
2	White textile	Cloth
3	Purple textile	Cloth
4	Dark blue textile	Cloth
5	Green textile	Cloth
6	Pink textile	Cloth
7	Turquoise textile	Cloth
8	Grey textile	Cloth
9	Orange textile	Cloth
10	Brown textile	Cloth
11	Red textile	Cloth

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)3185 8000

*The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.*

*The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.*

*This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.*

*ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.*



**SAMPLE PHOTO:**



-End Report-