

TEST REPORT

Test Report # 20H-006416 Date of Report Issue: October 15, 2020
Date of Sample Received: October 5, 2020 Pages: Page 1 of 11

CLIENT INFORMATION:

Company: Numo Manufacturing
Recipient: Rebecca Williams
Recipient Email: rwilliams@numomfg.com



SAMPLE INFORMATION:

Description: B740 - WHITE, BLACK, COBALT
Assortment: - Purchase Order Number: -
SKU/style No.: - Toy Co./Agency: -
Factory/Supplier/Vendor: Numo Manufacturing Country of Origin: China
Country of Distribution: - Labeled Age Grade: -
Quantity Submitted: 12 pcs per style Recommended Age Grade: -
Testing Period: 10/06/2020 – 10/15/2020 Tested Age Grade: -

OVERALL RESULT:

 **PASS**

Refer to page 2 for test result summary and appropriate notes.

QIMA Testing (HK) Limited



Loska Yeung Lok Ka
Assistant Manager, Chemical Laboratory

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, HKSAR, China ♦ Tel: (852)3185 8000.
The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. ANAB is recognized by ILAC, APAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the [QIMA decision rule](#).

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	Client's Requirement, Total Cadmium in Glass and Ceramic Materials ^{#φ}
PASS	California Proposition 65, Leachable Lead and Cadmium from Food Contact Articles – Interior
PASS	FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, HKSAR, China ♦ Tel: (852)3185 8000.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. ANAB is recognized by ILAC, APAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the [QIMA decision rule](#).

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

DETAILED RESULTS:

Client's Requirement, Total Cadmium in Glass and Ceramic Materials

Test Method: In-House Method^{#φ}
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	4	5	6	---	---	Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Cadmium (Cd)	ND	ND	ND	---	---	40
Conclusion	PASS	PASS	PASS	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, HKSAR, China ♦ Tel: (852)3185 8000.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

ANAB is recognized by ILAC, APAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the [QIMA decision rule](#).

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

DETAILED RESULTS:

California Proposition 65, Leachable Lead and Cadmium from Food Contact Articles – Interior

Test Method: ASTM C738-94(Reapproved 2016)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1A	1B	1C	1D	1E	1F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	410	410	410	410	410	410		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	0.189
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	0.100
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS		

Note:

mL = Millilitres
 mg/L (Milligrams per litre) = ppm (Parts per million)
 NA = Not applicable
 LT = Less than
 ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	0.189	0.100
	Flatware (Average of 6)	0.5	0.226
	Large Hollowware (Any of 6)	0.049	0.100
	Small Hollowware (Any of 6)	0.189	0.100
	Pitchers (Any of 6)	0.049	0.100

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, HKSAR, China ♦ Tel: (852)3185 8000.
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.
 ANAB is recognized by ILAC, APAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the [QIMA decision rule](#).

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

DETAILED RESULTS:

California Proposition 65, Leachable Lead and Cadmium from Food Contact Articles – Interior

Test Method: ASTM C738-94(Reapproved 2016)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	2A	2B	2C	2D	2E	2F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	410	410	410	410	410	410		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	0.189
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	0.100
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS		

Note:

mL = Millilitres
 mg/L (Milligrams per litre) = ppm (Parts per million)
 NA = Not applicable
 LT = Less than
 ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	0.189	0.100
	Flatware (Average of 6)	0.5	0.226
	Large Hollowware (Any of 6)	0.049	0.100
	Small Hollowware (Any of 6)	0.189	0.100
	Pitchers (Any of 6)	0.049	0.100

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, HKSAR, China ♦ Tel: (852)3185 8000.
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. ANAB is recognized by ILAC, APAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the [QIMA decision rule](#).

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

DETAILED RESULTS:

California Proposition 65, Leachable Lead and Cadmium from Food Contact Articles – Interior

Test Method: ASTM C738-94(Reapproved 2016)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	3A	3B	3C	3D	3E	3F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	410	410	410	410	410	410		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	0.189
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	0.100
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS		

Note:

mL = Millilitres
 mg/L (Milligrams per litre) = ppm (Parts per million)
 NA = Not applicable
 LT = Less than
 ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	0.189	0.100
	Flatware (Average of 6)	0.5	0.226
	Large Hollowware (Any of 6)	0.049	0.100
	Small Hollowware (Any of 6)	0.189	0.100
	Pitchers (Any of 6)	0.049	0.100

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, HKSAR, China ♦ Tel: (852)3185 8000.
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.
 ANAB is recognized by ILAC, APAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the [QIMA decision rule](#).

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

DETAILED RESULTS:

FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior

Test Method: ASTM C738-94(Reapproved 2016)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1A	1B	1C	1D	1E	1F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	410	410	410	410	410	410		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	0.5
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS		

Note:
 mL = Millilitres
 mg/L (Milligrams per litre) = ppm (Parts per million)
 NA = Not applicable
 LT = Less than
 ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	0.5	0.5
	Flatware (Average of 6)	0.5	3.0
	Large Hollowware (Any of 6)	0.25	1.0
	Small Hollowware (Any of 6)	0.5	2.0
	Pitchers (Any of 6)	0.25	0.5

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, HKSAR, China ♦ Tel: (852)3185 8000.
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.
 ANAB is recognized by ILAC, APAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the [QIMA decision rule](#).

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

DETAILED RESULTS:

FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior

Test Method: ASTM C738-94(Reapproved 2016)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	2A	2B	2C	2D	2E	2F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	410	410	410	410	410	410		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	0.5
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS		

Note:
 mL = Millilitres
 mg/L (Milligrams per litre) = ppm (Parts per million)
 NA = Not applicable
 LT = Less than
 ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

	Category	Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	0.5	0.5
	Flatware (Average of 6)	0.5	3.0
	Large Hollowware (Any of 6)	0.25	1.0
	Small Hollowware (Any of 6)	0.5	2.0
	Pitchers (Any of 6)	0.25	0.5

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, HKSAR, China ♦ Tel: (852)3185 8000.
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. ANAB is recognized by ILAC, APAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the [QIMA decision rule](#).

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

DETAILED RESULTS:

FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior

Test Method: ASTM C738-94(Reapproved 2016)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	3A	3B	3C	3D	3E	3F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	410	410	410	410	410	410		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	0.5
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS		

Note:
 mL = Millilitres
 mg/L (Milligrams per litre) = ppm (Parts per million)
 NA = Not applicable
 LT = Less than
 ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

	Category	Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	0.5	0.5
	Flatware (Average of 6)	0.5	3.0
	Large Hollowware (Any of 6)	0.25	1.0
	Small Hollowware (Any of 6)	0.5	2.0
	Pitchers (Any of 6)	0.25	0.5

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, HKSAR, China ♦ Tel: (852)3185 8000.
 The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. ANAB is recognized by ILAC, APAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the [QIMA decision rule](#).

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	Blue printed dull white ceramic	Interior of mug (Cobalt style)
2	Black printed dull white ceramic	Interior of mug (Black style)
3	White printed dull white ceramic	Interior of mug (White style)
4	Blue printed dull white ceramic	Whole mug (Cobalt style)
5	Black printed dull white ceramic	Whole of mug (Black style)
6	White printed dull white ceramic	Whole of mug (White style)

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, HKSAR, China ♦ Tel: (852)3185 8000.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

ANAB is recognized by ILAC, APAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the [QIMA decision rule](#).

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

SAMPLE PHOTO:



-End Report-

QIMA Testing (HK) Limited ♦ 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, HKSAR, China ♦ Tel: (852)3185 8000.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. ANAB is recognized by ILAC, APAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

Test(s) marked with 'φ' was subcontracted to external laboratory.

The test result(s) and conclusion(s) in this report relate only to the sample(s) as received and method /regulation section(s) tested as described herein.

If it is not further specified in the report, the decision rule for stating conformity is based on the [QIMA decision rule](#).

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.